

REMARKS

The present amendment seeks to place the application in better conformance with U.S. practice. A new Abstract page is included herewith.

Entry of the amendment is requested.

Respectfully submitted,

By



Aron Preis
Attorney for Applicants
Reg. No. 29,426

Bayer Corporation
100 Bayer Road
Pittsburgh, Pennsylvania 15205-9741
(412) 777-8343
FACSIMILE PHONE NUMBER:
(412) 777-8363

s:/sr/ap0283

VERSION WITH MARKINGS TO SHOW CHANGES MADE

IN THE ABSTRACT:

Please add an abstract page reading as follows:

--THERMOFORMABLE POLYAMIDES

ABSTRACT OF THE DISCLOSURE

A reinforced polyamide molding composition is disclosed. Characterized in that its viscosity at a shear velocity of 10 s^{-1} is greater than 1000 Pas and at a shear velocity of 1000 s^{-1} is less than 300 Pas, at processing temperatures of 40 to 80°C above its melting point, the composition is particularly suitable for thermoforming applications.--

IN THE CLAIMS:

Cancel Claims 3, 4, 5 and 6.

Add the following:

- 7. A method of using the composition of Claim 1 comprising preparing an article by thermoforming.
8. A method of using the composition of Claim 2 comprising preparing an article by thermoforming.
9. A method of preparing an article comprising thermoforming a composition comprising
- E) 98 to 41 parts by weight of a thermoplastic partially crystalline polyamide, and
 - F) 2 to 50 parts by weight of reinforcing materials, and
 - G) 0.1 to 4 parts by weight of branching additives and/or additives raising the molecular weight and

- H) 0 to 5 parts by weight of further additives,
the sum of the parts by weight of A, B, C, D totalling 100.
10. The method of Claim 9 wherein C is a diepoxide.
11. A method of preparing an article comprising thermoforming a composition comprising
- A) 67 to 85 parts by weight of a thermoplastic partially crystalline polyamide
and
 - B) 15 to 30 parts by weight of reinforcing materials, and
 - C) 0.2 to 1 part by weight of branching additives and/or additives raising the
molecular weight,
 - D) 0.1 to 2 parts by weight of further additives,
the sum of the parts by weight of A, B, C and D totaling 100.
12. The method of Claim 11 wherein C is a diepoxide.
13. A molded article obtained by the method of Claim 7.
14. A molded article obtained by the method of Claim 8.1
15. A molded article obtained by the method of Claim 9.
16. A molded article obtained by the method of Claim 10.
17. A molded article obtained by the method of Claim 11.
18. A molded article obtained by the method of Claim 12.--

THERMOFORMABLE POLYAMIDESABSTRACT OF THE DISCLOSURE

A reinforced polyamide molding composition is disclosed. Characterized in that its viscosity at a shear velocity of 10 s^{-1} is greater than 1000 Pas and at a shear velocity of 1000 s^{-1} is less than 300 Pas, at processing temperatures of 40 to 80°C above its melting point, the composition is particularly suitable for thermoforming applications.